

Qingdao Hisheng New Material Co.,LTD

China
01/1/2021

Hisheng C5 Hydrocarbon Resin HP100

Data Document

Identifier Qingdao Hisheng New Material Co.,LTD

Description

Hisheng HP100 hydrocarbon resin premium aliphatic hydrocarbon resin which is designed to tackify a variety of adhesive polymers including EVA, Polyolefin, APAO, NR, SIS, butyl rubber etc. It could be used for hotmelt adhesives, solvent basis PSA and other adhesives products

Sales Specifications

Property	Unites	Range
Softening Point(Ring&Ball, °C)	95-105	ASTM E28
Color(Garden, 50% resins in toluene)	Max 3	ASTM D1544
Ash %	Max 0.05	ASTM D1063
WaxCloudingPoint(EVA/Resin/Wax=22.5/32.5/45) °C	Max 85	ASTM3236
Acid Value(KOHmg/g)	Max 0.1	ASTM D974

Packaging

25kgs small bags, with pallet or without pallet

625kgs woven bag with pallet

EndUseRequirements

If the finished article is intended for use in food contact and packaging applications, toys, or human contact areas, manufacturers of the final product should observe all relevant regulations. Some of these regulations require tests to be carried out on the final product, e.g. migration. These are the responsibility of the final product manufacturer. Information on the food packaging clearances of individual products is available.

SafetyandHandlingPrecautions

Read the Safety Data Sheet carefully and thoroughly before beginning any work.

LegalDisclaimer

We can not anticipate all circumstances, conditions or applications in which this information, our products, or the products of other suppliers in combination with our products maybe used. We accept no responsibility for results obtained by the application of this information or for the safety or suitability of our products, either alone or in combination with other products. The user of our products bears the responsibility of determining their suitability for a particular application or formulation, or determining that the products or their used on otinfringeany intellectual property. Unless otherwise stated in writing, WE MAKE NO WARRANTY REGARDING THE INFORMATION PROVIDED HERE IN OR OUR PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, FITNESS FOR APARTICULAR PURPOSE, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY. The buyer assumes all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

ForFurtherInformation

Qingdao Hisheng New Material Co.,LTD
ADD: 1st Floor, East Office Building 45 Beijing Road, Qianwan Free Trade Port
Zone, Qingdao, China (Shangdong) Pilot Free Trade Zone 2022-1098 (A)
Website: www.hishengchem.cn

Email : Business@hishengchem.cn

Tel: +86 18562651969